## IN THE CLAIMS:

The text of all pending claims are set forth below. Cancelled and withdrawn claims are indicated with claim number and status only. The claims as listed below show added text with underlining and deleted text with strikethrough. The status of each claim is indicated with one of (original), (currently amended), (previously amended), (cancelled), (withdrawn), (new), (previously added), (reinstated - formerly claim #), (previously reinstated), (re-presented - formerly dependent claim #) or, (previously re-presented).

Please ADD claim 26 in accordance with the following:

- 1. (original): A photocatalyst composition comprising:
  - (A) modified photocatalyst particles,

said modified photocatalyst particles (A) being prepared by subjecting particles of a photocatalyst (a) to a modification treatment with at least one modifier compound (b) selected from the group consisting of different compounds each of which independently comprises at least one structural unit selected from the group consisting of a triorganosilane unit represented by formula (1), a monooxydiorganosilane unit represented by formula (2), and a dioxyorganosilane unit represented by formula (3):

$$R_3Si-$$
 (1)

wherein each R independently represents a straight chain or branched  $C_1$ - $C_{30}$  alkyl group, a  $C_5$ - $C_{20}$  cycloalkyl group, a straight chain or branched  $C_1$ - $C_{30}$  fluoroalkyl group, a straight chain or branched  $C_2$ - $C_{30}$  alkenyl group, a phenyl group, a  $C_1$ - $C_{20}$  alkoxy group or a hydroxy group,

$$-(R2SiO)-$$
 (2)

wherein each R is as defined for formula (1), and

wherein R is as defined for formula (1), and

(B) a binder component which comprises a phenyl group-containing silicone (BP), optionally containing an alkyl group, represented by formula (4):

$$R_{p}^{1}R_{q}^{2}X_{r}SiO_{(4-p-q-r)/2}$$
 (4)

wherein:

the or each  $R^1$  represents a phenyl group, and the or each  $R^2$  independently represents a straight chain or branched  $C_1$ - $C_{30}$  alkyl group, a  $C_5$ - $C_{20}$  cycloalkyl group or a straight chain or branched  $C_2$ - $C_{30}$  alkenyl group;

the or each X independently represents a hydrogen atom, a hydroxyl group, a  $C_1$ - $C_{20}$  alkoxy group, a  $C_1$ - $C_{20}$  acyloxy group, an aminoxy group, a  $C_1$ - $C_{20}$  oxime group or a halogen atom; and

p, q and r satisfy the following relationships:

$$0 ,$$

$$0 \le q < 4$$

$$0 \le r < 4$$
,

$$0 < (p + q + r) < 4$$
, and

$$0.05 \le p/(p+q) \le 1$$
.

- 2. (original): The composition according to claim 1, wherein the or each R of each of formulae (1) to (3) independently represents a straight chain or branched  $C_1$ - $C_{30}$  alkyl group, a  $C_5$ - $C_{20}$  cycloalkyl group, a straight chain or branched  $C_1$ - $C_{30}$  fluoroalkyl group, a straight chain or branched  $C_2$ - $C_{30}$  alkenyl group or a  $C_1$ - $C_{20}$  alkoxy group.
- 3. (original): The composition according to claim 1 or 2, wherein said phenyl group-containing silicone (BP) is a phenyl group-containing silicone (BP1), containing no alkyl group, represented by formula (5):

$$R^{1}_{s}X_{t}SiO_{(4-s-t)/2}$$
 (5)

wherein:

the or each R<sup>1</sup> represents a phenyl group;

the or each X independently represents a hydrogen atom, a hydroxyl group, a  $C_1$ - $C_{20}$  alkoxy group, a  $C_1$ - $C_{20}$  acyloxy group, an aminoxy

group, a  $C_1$ - $C_{20}$  oxime group or a halogen atom; and s and t satisfy the following relationships:

$$0 < s < 4$$
,

$$0 \le t < 4$$
, and

$$0 < (s + t) < 4$$
.

4. (original): The composition according to claim 1 or 2, wherein said binder component (B) further comprises an alkyl group-containing silicone (BA) represented by formula (6):

$$R^{2}_{u}X_{v}SiO_{(4-u-v)/2}$$
 (6)

wherein:

the or each  $R^2$  independently represents a straight chain or branched  $C_1$ - $C_{30}$  alkyl group, a  $C_5$ - $C_{20}$  cycloalkyl group or a straight chain or branched  $C_2$ - $C_{30}$  alkenyl group;

the or each X independently represents a hydrogen atom, a hydroxyl group, a  $C_1$ - $C_{20}$  alkoxy group, a  $C_1$ - $C_{20}$  acyloxy group, an aminoxy group, a  $C_1$ - $C_{20}$  oxime group or a halogen atom; and u and v satisfy the following relationships:

$$0 < u < 4$$
,

$$0 \le v < 4$$
, and

$$0 < (u + v) < 4$$
.

5. (previously presented): The composition according to claim 1 or 2, wherein said binder component (B) comprises a phenyl group-containing silicone (BP1), containing no alkyl group, represented by formula (5):

$$R^{1}_{s}X_{t}SiO_{(4-s-t)/2}$$
 (5)

wherein:

the or each R<sup>1</sup> represents a phenyl group;

the or each X independently represents a hydrogen atom, a hydroxyl group, a  $C_1$ - $C_{20}$  alkoxy group, a  $C_1$ - $C_{20}$  acyloxy group, an aminoxy group, a  $C_1$ - $C_{20}$  oxime group or a halogen atom; and s and t satisfy the following relationships:

$$0 < s < 4$$
,

 $0 \le t < 4$ , and

$$0 < (s + t) < 4$$
; and

an alkyl group-containing silicone (BA) represented by formula (6):

$$R^{2}_{u}X_{v}SiO_{(4-u-v)/2}$$
 (6)

wherein:

the or each  $R^2$  independently represents a straight chain or branched  $C_1$ - $C_{30}$  alkyl group, a  $C_5$ - $C_{20}$  cycloalkyl group or a straight chain or

branched C2-C30 alkenyl group;

the or each X independently represents a hydrogen atom, a hydroxyl group, a  $C_1$ - $C_{20}$  alkoxy group, a  $C_1$ - $C_{20}$  acyloxy group, an aminoxy group, a  $C_1$ - $C_{20}$  oxime group or a halogen atom; and u and v satisfy the following relationships:

$$0 < u < 4$$
,

$$0 \le v < 4$$
, and

$$0 < (u + v) < 4$$
.

6. (previously presented): The composition according to claim 4, wherein said alkyl group-containing silicone (BA) comprises a monooxydiorganosilane unit (D) represented by formula (7) and a dioxyorganosilane unit (T) represented by formula (8):

$$-(R22SiO)- (7)$$

wherein each  $R^2$  independently represents a straight chain or branched  $C_1$ - $C_{30}$  alkyl group, a  $C_5$ - $C_{20}$  cycloalkyl group or a straight chain or branched  $C_2$ - $C_{30}$  alkenyl group, and

wherein R<sup>2</sup> is as defined for formula (7).

- 7. (previously presented): The composition according to claim 3, wherein said phenyl group-containing silicone (BP1) has a weight average molecular weight of from 500 to 10,000, as measured by gel permeation chromatography using a calibration curve obtained with respect to standard polystyrenes.
- 8. (previously presented): The composition according to claim 4, wherein said alkyl group-containing silicone (BA) has a weight average molecular weight of from 500 to 10,000, as measured by gel permeation chromatography using a calibration curve obtained with respect to standard polystyrenes.
- 9. (previously presented): The composition according to claim 1 or 2, wherein said modified photocatalyst particles (A) have a number average particle diameter of 400 nm or less.
- 10. (previously presented): The composition according to claim 1 or 2, wherein said photocatalyst particles (a) are titanium oxide particles.
- 11. (previously presented): The composition according to claim 1 or 2, wherein said modifier compound (b) is an Si-H group-containing silicon compound (b1) represented by formula (9):

$$H_xR_ySiO_{(4-x-y)/2}$$
 (9)

wherein:

the or each R independently represents a straight chain or branched  $C_1$ - $C_{30}$  alkyl group, a  $C_5$ - $C_{20}$  cycloalkyl group, a straight chain or branched  $C_1$ - $C_{30}$  fluoroalkyl group, a straight chain or branched  $C_2$ - $C_{30}$  alkenyl group, a phenyl group, a  $C_1$ - $C_{20}$  alkoxy group or a hydroxy group, and

x and y satisfy the following relationships:

$$0 < x < 4$$
,

$$0 < y < 4$$
, and

$$(x+y)\leq 4.$$

12. (original): The composition according to claim 11, wherein said Si-H group-containing silicon compound (b1) comprises at least one compound selected from the group consisting of:

a mono Si-H group-containing silicon compound represented by formula (10):

wherein each  $R^3$  independently represents a chain or branched  $C_1$ - $C_{30}$  alkyl group, a straight chain or branched  $C_2$ - $C_{30}$  alkenyl group, a  $C_5$ - $C_{20}$  cycloalkyl group, a straight chain or branched  $C_1$ - $C_{30}$  fluoroalkyl group, a phenyl group or a siloxy group represented by formula (13):

$$-O-(R42SiO)m-SiR43 (13)$$

wherein each  $R^4$  independently represents a straight chain or branched  $C_1$ - $C_{30}$  alkyl group, a  $C_5$ - $C_{20}$  cycloalkyl group, a straight chain or branched  $C_1$ - $C_{30}$  fluoroalkyl group, a straight chain or branched  $C_2$ - $C_{30}$  alkenyl group or a phenyl group; and m is an integer which satisfies the formula:  $0 \le m \le 1000$ ,

a silicon compound, having Si-H groups at both terminals thereof, represented by formula (11):

$$H-(R32SiO)n-SiR32-H (11)$$

wherein  $R^3$  is as defined for formula (10); and n is an integer which satisfies the formula:  $0 \le n \le 1000$ , and an H silicone represented by formula (12):

$$(R^3HSiO)_a(R^3_2SiO)_b(R^3_3SiO_{1/2})_c$$
 (12)

wherein:

R<sup>3</sup> is as defined for formula (10); and

a is an integer of 1 or more, b is an integer of 0 or more, and a and b satisfy the following relationship:  $(a + b) \le 10000$ , and c is 0 or 2, and wherein when (a + b) is an integer of 2 or more and c = 0, said H silicone of formula (12) is a cyclic silicone, and when c = 2, said H silicone of formula (12) is a straight chain silicone.

- 13. (previously presented): The composition according to claim 1 or 2, which further comprises a resin.
- 14. (previously presented): The composition according to claim 1 or 2, which is a film.
- 15. (original): The composition according to claim 14, which is anisotropic with respect to the distribution of the modified photocatalyst particles (A), wherein the concentration of the modified photocatalyst particles (A) increases from one surface of the film toward the other surface of the film.
- 16. (previously presented): The composition according to claim 1 or 2, which is a shaped article.
- 17. (original): The composition according to claim 16, which is anisotropic with respect to the distribution of the modified photocatalyst particles (A), wherein the concentration of the modified photocatalyst particles (A) increases from the inner

portion of the shaped article toward the surface of the shaped article.

18. (original): The composition according to claim 4, which is a film which has a microphase separation structure with respect to said phenyl group-containing silicone (BP) and said alkyl group-containing silicone (BA).

- 19. (original): The composition according to claim 18, which is anisotropic with respect to the distribution of the modified photocatalyst particles (A), wherein the concentration of the modified photocatalyst particles (A) increases from one surface of the film toward the other surface of the film.
- 20. (original): The composition according to claim 4, which is a shaped article which has a microphase separation structure with respect to said phenyl groupcontaining silicone (BP) and said alkyl group-containing silicone (BA).
- 21. (original): The composition according to claim 20, which is anisotropic with respect to the distribution of the modified photocatalyst particles (A), wherein the concentration of the modified photocatalyst particles (A) increases from the inner portion of the shaped article toward the surface of the shaped article.
- 22. (previously presented): A functional composite comprising a substrate and a film formed on said substrate, said film comprising the composition of claim 1 or 2.

23. (original): The functional composite according to claim 22, wherein said film is anisotropic with respect to the distribution of the modified photocatalyst particles (A), wherein the concentration of the modified photocatalyst particles (A) increases from a surface of the film which contacts the substrate toward the other, exposed surface of the film.

- 24. (original): A functional composite comprising a substrate and a film formed on said substrate, said film comprising the composition of claim 4 and having a microphase separation structure with respect to said phenyl group-containing silicone (BP) and said alkyl group-containing silicone (BA).
- 25. (original): The functional composite according to claim 24, wherein said film is anisotropic with respect to the distribution of the modified photocatalyst particles (A), wherein the concentration of the modified photocatalyst particles (A) increases from a surface of the film which contacts the substrate toward the other, exposed surface of the film.
- 26. (new): The composition according to claim 2, wherein the or each R of each of formulae (1) to (3) independently represents a straight chain or branched  $C_1$ - $C_{30}$  alkyl group, a  $C_5$ - $C_{20}$  cycloalkyl group, a straight chain or branched  $C_1$ - $C_{30}$  fluoroalkyl group or a straight chain or branched  $C_2$ - $C_{30}$  alkenyl group.